ADESTOR LASER 70 REMOVABLE RA678 KL55

Country of manufacture:	Spain
Product components	
Face (LASER 70):	Uncoated wood-free paper guaranteed for laser printing.
Adhesive (RA678):	Acrylic removable adhesive with clean removability from most surfaces. Trial is recommended when using this adhesive in new or unknown surfaces.
Liner (KL55):	Kraft liner guaranteed for laser printing. For the conversion of reels to sheets.
Printing techniques:	Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, screen printing, hot stamping, laser, inkjet printing and photocopying machines.



FACE

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	70	± 4%
Thickness	ISO 534	μm	90	± 5
Brightness ISO	ISO 2470-2	%	103	± 2
Whiteness CIE	ISO 11475	%	143	± 5
Opacity	ISO 2471	%	91	-2
Tensile strength MD/CD	ISO 1924-2	kN/M	≥ 3,2 / ≥ 1,9	- 2

ADHESIVE

Property	Norm	Units	Value	Tolerance
Adhesion (Peel stainless steel 1 week)	FTM 1	N/25mm	1,7	1 - 2,9
Shear (1kg, in²/glass)	FTM 8	Min	120	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	1,2	0,7 - 1,7
Minimum labelling temperature		°C	5	
Minimum service temperature		°C	-20	
Maximum service temperature		°C	80	

LINER

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	55	52,5 - 57,5
Thickness	ISO 534	μm	56	52 - 60
Tensile strength MD/CD	ISO 1924-2	kN/M	≥ 3,8 / ≥ 1,6	



Face

- Contact with Foodstuff (BfR XXXVI) Face and Liner (paper)
- Electric and electronic equipment (RoHS)
- Packaging and packaging waste Directive 94/62/CE
- Toy Safety European directive 2009/48/CE

Adhesive

- EN 71-3 Toy Safety
- Packaging and packaging waste Directive 94/62/CE

Liner

- Contact with Foodstuff (BfR XXXVI) Face and Liners (paper)
- Electric and electronic equipment (RoHS) Directive 2002/95/CE
- Packaging and packaging waste Directive 94/62/CE
- EN 71-3 Toy Safety
- EN 71-9 Toy Safety

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Shelf Life: From the date of manufacture 1 year in 20°C and RH 50%. These characteristics are average values supplied for guidance purposes.

Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.

