

PMC DT TOP NA PP34F WG62

Country of manufacture:	Thailand
--------------------------------	----------

Applications:	Designed for use in thermal sensitive printing systems. Typical applications are bar code labels for food packaging; industrial bar coding and tracking where good long-term smudge resistance is required.
----------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Product components

Face:	Premium top coated thermal paper with excellent image preservation offering superior resistance and sharp image to moisture, oil and plastisizer.
-------	---------------------------------------------------------------------------------------------------------------------------------------------------

Adhesive (PP34F):	High initial tack, general-purpose permanent adhesive. Featuring excellent adhesion to low surface energy substrates.
-------------------	-----------------------------------------------------------------------------------------------------------------------

Liner (WG62):	Super calendered White Glassine paper
---------------	---------------------------------------



TECHNICAL SPECIFICATIONS

Property	Grammage	Thickness
Face	70gsm	72 micron (2,8 mil)
Liner	58gsm	51 micron (2 mil)
Total	152gsm, $\pm 10\%$	146 micron, $\pm 10\%$

ADHESIVE

Property			
Initial Tack	Glass	FTM 9	$\geq 13,5$ N/25 mm
Initial Tack	Stainless Steel	FTM 9	$\geq 12,5$ N/25 mm
Adhesion to	Stainless Steel	FTM 2 20 minute 90° peel	$\geq 7,5$ N/25 mm
Minimum Service Temperature		-20 °C	-4 °F
Maximum Service Temperature		80 °C	176 °F
Minimum Application Temperature		5 °C	41 °F

CERTIFICATES

- US FDA 21 CFR 175.105 (Adhesive) for indirect food contact packaging and processing.
- European Toy Safety Legislation 88/278/EEC, CEN EN71, Part 4

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Shelf Life: 1 year if store in 22°C and 50% RH condition. The product must be stored in shady or cool place and do not expose to sunlight directly.

These characteristics are average values supplied for guidance purposes.

Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.

