

PMC FLUORO ORANGE PP33F WG62

Country of manufacture: Thailand

Applications: General-purpose label designed for eye-catching applications such as instructional, promotional and POS label. It is advisable to test the product with the end-use conditions during the qualification to ensure it meets specific requirements.

Product components

Face (FLUORO ORANGE): One sided fluorescent coloured coated paper.

Adhesive (PP33F): General-purpose permanent adhesive, with very good water and aging resistance. Featuring excellent adhesion to low surface energy substrates.

Liner (WG62): Super calendared White Glassine paper.

TECHNICAL SPECIFICATIONS

| Property | Grammage | Thickness |
|----------|---------------------|------------------------|
| Face | 72gsm | 80 micron (3,1 mil) |
| Liner | 60gsm | 54 micron (2,1 mil) |
| Total | 153 gsm, $\pm 10\%$ | 154 micron, $\pm 10\%$ |

ADHESIVE

| Property | | | | |
|---------------------------------|-----------------|--------------------------|-------------|---------|
| Initial Tack | Glass | FTM 9 | $\geq 12,5$ | N/25 mm |
| Initial Tack | Stainless Steel | FTM 9 | ≥ 12 | N/25 mm |
| Adhesion to | Stainless Steel | FTM 2 20 minute 90° peel | $\geq 6,5$ | N/25 mm |
| Minimum Service Temperature | | -40 °C | -40 °F | |
| Maximum Service Temperature | | 120 °C | 248 °F | |
| Minimum Application Temperature | | -5 °C | 23 °F | |

CERTIFICATES

- US FDA 21 CFR 175.105 (Adhesive) for indirect food contact packaging and processing.
- European Toy Safety Legislation 88/278/EEC, CEN EN71, Part 3

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Shelf Life: From the date of manufacture 1 year in 22°C and RH 50%. These characteristics are average values supplied for guidance purposes.

Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.

