



TECHNICAL SPECIFICATION SHEET

Updated: March 2017

PRODUCT

PMC PREMIUM GLOSS HI WHITE PP30F WG62

CATEGORY

Utility

MANUFACTURER

PMC Label Materials Co., Ltd.

WEBSITE

www.pmclabel.com

COUNTRY OF MANUFACTURE

Thailand

APPLICATIONS

Mainly used for commercial inkjet printing. Universally printable with dye inks. A list of printers showing compatibility with pigmented ink. We recommend checking suitability of this product on your printer before using. It is advisable to test the product with the end-use conditions during the qualification to ensure it meets specific requirements.

PRODUCT COMPONENTS

| | |
|--|--|
| Facestock (PREMIUM GLOSS HI WHITE): | Super white with gloss surface, one side cast coated and mirror finished printing paper. |
| Adhesive (PP30F): | General purpose permanent adhesive. Featuring excellent adhesion to low surface energy substrates. |
| Liner (WG62): | Super-calendered White glassine paper. |

Please note: B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

B&F Papers are committed to being an environmentally responsible company. www.bfpapers.co.nz



TECHNICAL SPECIFICATIONS

| | Grammage | Thickness |
|-----------|-----------------|----------------------|
| Facestock | 87gsm | 104 micron (4.1 mil) |
| Liner | 60gsm | 55 micron (2.2mil) |
| Total | 168gsm , ±10% | 179micron , ±10% |

ADHESIVE PHYSICAL PROPERTIES

| | | | | |
|--------------|-----------------|--------------------------|--------|----------|
| Initial Tack | Glass | FTM 9 | ≥ 12.5 | N/25 mm. |
| Initial Tack | Stainless Steel | FTM 9 | ≥ 12.0 | N/25 mm. |
| Adhesion to | Stainless Steel | FTM 2 20 minute 90° peel | ≥ 6.5 | N/25 mm. |

| | | |
|---------------------------------|--------|--------|
| Minimum Service Temperature | -40 °C | -40 °F |
| Maximum Service Temperature | 120 °C | 248 °F |
| Minimum Application Temperature | -5 °C | 23 °F |

Shelf Life: 1 year if store in 22°C and 50% RH condition. The product must be stored in a shady or cool place and not directly exposed to sunlight. These characteristics are average values supplied for guidance purposes

Note: It is recommended that all pressure sensitive materials are trialled prior to printing.

Please note: B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

B&F Papers are committed to being an environmentally responsible company. www.bfpapers.co.nz